

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### DESCRIPTION

**Diamapro Systems® Diamapro-Industrial Flake System** has urethane polymer cement (UPC) chemistry used with decorative flake that brings together color and industrial durability in one package. Its urethane cement technology works in high moisture environments. It is suited to withstand continuous industrial traffic in high use environments when a top-of-the-line decorative flake system is required. The increased slip resistance will help ensure a safer floor compared to a non-treated surface.

The **Diamapro Systems® Diamapro-Industrial Flake System** is available in fast and slow cure formulations. The selection is based on all environmental conditions. With each cure time formulation, the cured film performance criteria will remain the same, only the working and return to service times change.

### RECOMMENDED USES

- Industrial Facilities
- High Traffic Commercial Spaces
- Auto Garages
- Industrial Utility rooms

### ADVANTAGES

- **Diamapro Systems® Diamapro-Flow RC** can withstand up to 15 lbs. of vapor.
- **Diamapro Systems® Diamapro-Poxy MVR** can withstand up to 25 lbs. of vapor.
- Meets USDA, FDA, EPA, and SCAQMD Standards
- Eligible for LEED Points: Made in California from Partially Recycled Materials
- Adheres to Concrete, Wood, Metal, Non-glazed tiles.
- Antibacterial
- Easy Installation
- Extreme Temperature Resistance, 0–200°F
- Low Maintenance
- Scratch Resistance
- Waterproofing

### STORAGE, HANDLING AND DISPOSAL

- Storage:
  - Store materials in a cool (60-80°F), dry place out of direct sunlight.
  - DO NOT allow water into materials unless instructed to do so.
- Handling:
  - Safety Data Sheets must be adhered to.
  - No personnel may touch, relocate, or use materials without proper training.
  - All materials must be considered dangerous substances without firsthand knowledge.
  - Eating, smoking, or drinking is not allowed near materials.
- Disposal:
  - Follow federal, local, and building requirements for waste disposal.

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### LIMITATIONS

- UV Stability
  - Coating will amber over time.
  - If color stability is important, contact the Diamapro Systems® Technical Representative
- Primer Coat
  - May be required when the substrate is highly absorbent.
  - When outgassing is suspected or prevalent.
  - When the concrete is very porous or in poor condition.
- All concrete repairs must be completed before installation.
- Do not let material puddle on floor.
- An onsite mockup should be installed to ensure desired results.
- When temperatures increase, material cures faster.
- Adhere to the Diamapro Systems® Dew Point Calculation Chart.
- DO NOT apply under direct sunlight.
- DO NOT install under inclement weather conditions.
- Application times are based on test results compiled by lab technicians in a controlled setting.
- Coverage rates are for estimating purposes only.
  - Factors such as waste, unusual/abnormal substrate conditions, and other unforeseen job-site conditions may affect actual product yields and are the responsibility of the installer.
- For best results, apply when application temperatures and relative humidity are low.
- **Diamapro Systems® Diamapro-Thane NGU**
  - Do not apply single coat greater than 10-20 mils - 80-160 sq.ft./gal.).
- Diamapro Systems® Diamapro-Thane HPU
  - Must be applied over Diamapro Systems® Diamapro-Thane NGU.
  - Do not apply single coat greater than 5 mils thick (320 sf per gallon).
  - Do not install directly over moisture-sensitive concrete, vinyl chip, 30-grit or larger quartz, or 80-mesh or larger aluminum oxide.

### STORAGE AND APPLICATION TEMPERATURES

<b>Ideal Storage Environment</b>	Dry, Out of Direct Sunlight, 60-80°F
<b>Material Temperature During Application</b>	50-70°F and 5°F Above Dew Point
<b>Minimum Substrate Temperature During Application</b>	5°F Above Dew Point
<b>Recommended Application Temperature</b>	60-90°F, <80% RH (Relative Humidity)



# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### TECHNICAL DATA

Diamapro Systems® Diamapro-Flow RC Slow Cure (Base Coat and Optional Primer)

Application Temperature	60-90°F, <80% RH		50F, 50% RH	70°F, 50% RH	100°F, 50% RH
Working Time	30 min.		40 min.	30 min.	20 min.
Recoat Time	12 hrs.		24 hrs.	12 hrs.	10 hrs.
Return to Service	24-36 hrs.		36 hrs.	24 hrs.	24 hrs.
Full Cure	7 days		7 days	7 days	7 days

Diamapro Systems® Diamapro-Thane NGU (High Wear Topcoat)

Product	Fast Cure	Slow Cure
Application Temperature	40-80F <40% RH	60-110F <90% RH
Working Time	15-20 min.	30-45 min.
Recoat Time	2-4 hours	6-8 hours
Return to Service	12 hours	48 hours
Full Cure	7 days	7 days

Diamapro Systems® Diamapro-Thane HPU (*Optional: High Performance Finish*)

Ambient Temperature	60-90°F, <70% RH	50°F, 30% RH	50°F, 75% RH	70°F, 50% RH	90°F, 20% RH	90°F, 80% RH
Working Time	20 min.	25-30 min.	10-15 min.	20 min.	15 min.	15 min.**
Recoat Window	4-6 hrs.	3-6 hrs.	2-6 hrs.	3-6 hrs.	2-6 hrs.	2-6 hrs.
Return to Service (Foot Traffic)	12 hrs.	12 hrs.	12 hrs.	12 hrs.	12 hrs.	12 hrs.
Full Cure (Vehicle Traffic)	5 days	5 days	5 days	5 days	5 days	5 days

\*\*Must add viscosity reducer.

### COLORANTS

- May affect working times.
- May reduce chemical resistance.
- May increase potential for stain.
- Coatings tested at ambient temperature over 1-3 days' exposure to chemical.
- To ensure desired results are achieved, products should be tested on site before installation.



# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### CHEMICAL AND STAIN RESISTANCE

1 = Best for chemical resistance: No adverse effects on fully cured coating; Remove within 24 hours.

2 = Low potential for stain: No adverse effects: Remove within 24 hours.

3 = High potential for stain or degradation: Must be removed within 24 hours of exposure.

NR = Not recommended

CHEMICAL	POLY	NGU	HPU	CHEMICAL	POLY	NGU	HPU
Acetic Acid 10%	1	1	1	Chromic Acid, 10%	1	1	1
Acetic Acid, 30%	2	2	2	Chromic Acid, 30%	1	1	1
Acetone	1	1	1	Citric Acid, 30%	1	1	1
Ammonia, 30%	1	1	1	Ethanol, 95%	1	1	1
Ammonium Hydroxide, 30%	1	1	1	Ethyl Acetate, 99%	1	1	1
Antifreeze (Coolant)	1	1	1	Formaldehyde, 37%	2	3	2
Benzene	1	1	1	Premium Gasoline	1	1	1
Benzyl Alcohol	1	1	1	Hydraulic Fluids	1	2	1
Betadine, 11%	1	1	1	Hydrochloric Acid, 10%	1	1	1
Boric Acid, 4%	1	1	1	Hydrochloric Acid, 30%	3	3	3
Brake Fluid, DOT 3	1	1	1	Hydrofluoric Acid, 10%	1	1	1
Hydrofluoric Acid, 30%	3	3	3	Phosphoric Acid, 20%	1	2	1
Hydrogen Peroxide, 10%	1	1	1	Potassium Hydroxide, 30%	1	1	1
Hydrogen Peroxide, 50%	1	1	1	Propylene Glycol	1	1	1
Iodine, 2%	3	3	3	Silver Nitrate, 20%	1	3	1
Isopropyl Alcohol	1	2	1	Sodium Chloride, 20%	1	1	1
Jet Fuel	1	1	1	Sodium Hydroxide 50%	1	1	1
Lactic Acid, 30% (Dairy Facility)	1	3	1	Sodium Hypochlorite 10%	1	1	1
Lime Juice	1	1	1	Sodium Hypochlorite 30%	2	2	2
Magnesium Hydroxide	1	1	1	Sodium Persulfate	3	3	3
MEK (Methyl Ethyl Ketone)	1	1	1	Sulfuric Acid, 37% (Battery Acid)	1	2	1
Methanol	1	1	1	Tannic Acid, 20%	2	3	2
Methylene Chloride	NR	NR	NR	Tartaric Acid, 10%	1	1	1
MIBK (Methyl Isobutyl Ketone)	1	1	1	Transmission Fluid	1	1	1
Mineral Oil	1	1	1	Urine, Dog or Cat	1	1	1
Motor Oil, SAE 30	1	1	1	Urea (Nitrogen-Rich Fertilizer)	1	1	1
Mineral Spirits	1	1	1	Vinegar, Distilled	1	1	1
Mustard, Yellow	1	1	1	Water (Hard Water from Well)	1	1	1
Nitric Acid, 30%	1	NR	1	Whisky	1	1	1
Oleic Acid	1	1	1	Wine, Cabernet Sauvignon	1	1	1
Oxalic Acid, 10%	1	1	1	Xylene	1	1	1

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### PROPERTIES WHEN FULLY CURED

#### Diamapro Systems® Diamapro-Flow RC (Base Coat)

PROPERTIES	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	70 mg loss
Abrasion Resistance with Anti-Slip	ASTM D4060	40-60 mg loss
Adhesion Strength	ASTM D4541	>500 psi, concrete failure
Compressive Strength	ASTM C579	7,000 psi
Flame Spread/ Critical Flux	ASTM E648	Class 1
Flame Spread/ Rate of Burning	ASTM D635	Self-extinguishing
Flexural Modulus of Elasticity	ASTM C580	3.5 x 10 <sup>6</sup> psi
Flexural Strength	ASTM C580	2,700 psi
Hardness (Shore D)	ASTM D2240	80
Impact Resistance	ASTM D2794	>160 in-lbs.
Indoor Air Quality	CA 01350	Compliant
Linear Shrinkage	ASTM C531	0.20%
Microbial Resistance	ASTM G21	Passes, 0 growth
Moisture Vapor Permeance	ASTM E96	0.15 perms
Tensile Strength	ASTM C307	2,000 psi
Thermal Coefficient of Linear Expansion	ASTM C531	2.0 x 10 <sup>-5</sup> in/in/°F
Thermal Shock Resistance	ASTM C484	50 cycles, no cracking
Water Absorption	ASTM C413	<0.10%

#### Diamapro Systems® Diamapro-Thane NGU (High Wear Topcoat)

PROPERTIES	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	15 mg loss
Adhesion Strength	ASTM D4541	400 psi, 100% Concrete failure
Adhesion Strength	ASTM D4541	n/a, vinyl failure
Adhesion Strength	ASTM D4541	n/a, natural quartz failure
Adhesion Strength	ASTM D4541	n/a, color quartz failure
Coefficient of Friction - Dry	ASTM D2047	0.7
Coefficient of Friction - Wet	ASTM D2047	0.6
Flame Spread/ Critical Flux	ASTM E648	Class 1
Flame Spread/ Rate of Burning	ASTM D635	Self-extinguishing
Flexibility/ Mandrel Bend	ASTM D522	Passes 1/8-in.
Gloss, 60°	ASTM D523	90
Hardness (König Hardness)	ASTM D4366	150
Impact Resistance	ASTM D2794	120 in-lbs.
Indoor Air Quality	CA 01350	Compliant
Microbial Resistance	ASTM G21	Passes, 0 growth
Tensile Elongation at Break	ASTM D2370	5%
Tensile Strength	ASTM D2370	6,000 psi
UV Resistance	ASTM D4587	High (Level 3)
Water Absorption	ASTM D570	<0.05
Yellowing Resistance	ASTM G154	< 3.0 ΔE, gray (color tested for visible changes)

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### Diamapro Systems® Diamapro-Thane HPU (Optional: High Performance Finish)

PROPERTIES	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	10 mg loss
Adhesion Strength	ASTM D4541	>400 psi, epoxy failure
Coefficient of Friction- Dry	ASTM D2047	0.7
Coefficient of Friction - Wet	ASTM D2047	0.6
Flame Spread/ Critical Flux	ASTM E648	Class 1
Flame Spread/ Rate of Burning	ASTM D635	Self-extinguishing
Flexibility/ Mandrel Bend	ASTM D522	Passes 1/8-in.
Gloss, 60°	ASTM D523	80+
Hardness (König Hardness)	ASTM D4366	170
Impact Resistance	ASTM D2794	120 in-lbs.
Indoor Air Quality	CA 01350	Compliant
Microbial Resistance	ASTM G21	Passes, 0 growth
Tensile Elongation at Break	ASTM D2370	8%
Tensile Strength	ASTM D2370	6,500 psi
UV Resistance	ASTM D4587	Mid to High (Level 2)
Water Absorption	ASTM D570	<0.05

## INSTALLATION INSTRUCTIONS

### SURFACE PREPARATION

- Mechanically remove all release agents, curing compounds, salts, efflorescence, grease, oil, dust, and other bond inhibiting contaminants.
- New concrete must be a minimum of 30 days old.
- Mechanically prepare concrete (grind or shotblast) to an ICRI CSP 3.
- Adhere to ICRI (International Concrete Repair Institute) current standards.
- Complete all repairs during the surface preparation step.
- Fill all joints during the surface preparation step.
- Vacuum well to remove all imbedded dust created during the surface preparation step.

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### COMPONENTS

- Diamapro Diama-Flow RC Slow
  - Part A: 12 lbs.
  - Part B: 12 lbs.
  - Part C: 12 lbs.
  - 6-Gallon Kit
- Decorative Flake
  - 40 lbs. boxes
    - Small – 1/8"
    - Standard -1/4"
- Diamapro Systems® Diama-Thane NGU
  - Part A: 1 or 5 gallons
  - Part B: 1 or 5 gallons
  - 2- or 10-gallon Unit
- Diamapro Systems® Diama-Thane HPU
  - Gloss:
    - Part A – ½ gal.
    - Part B – 1 gal.
    - 1.5 gal. mixed unit
  - Satin
    - Part A – 1 qt.
    - Part B – 1 gal.
    - 1.25 gal. mixed unit

### MIXING

- Select a well-ventilated area outside of application zone and out of direct sunlight.
- Ideal mixing station is 4-by-4 feet or larger level surface protected by cardboard or poly sheets.
- Mix carefully to avoid introducing bubbles into the mixture by keeping the mixing fins below the surface.
- All mixing vessels must be clean.
- Pour entire contents of Part A into mixing vessel before adding other components.
- Add Part B into Part A
- Change mixing buckets every 2-5 batches.
- Scrape the mixing vessel sides and bottom to ensure coating is thoroughly blended.
  - Buildup on bucket or transfer of buildup to a new batch affects the coating's overall appearance and may shorten a product's working time.
- Make sure that material stays thoroughly mixed throughout application.
  - Do NOT allow any material (sand for texture) to settle at the bottom of the mixing vessel.
- Only combine products within the same product line.
- **Optional Colorant and/or Texture Additives:**
  - When adding color and/or texture: Combine additive(s) with Part A and mix until consistency and color are uniform.
  - Pour entire contents of Part B into Part A and mix.
  - TOTAL MIX TIME: 2 minutes.

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### COVERAGE RATES

Application	Coverage Rate
Base Coat – Diamapro Systems® Diamapro-Flow RC	8-12 mils 135–200 SF/gal
Decorative Flake 1/8”-1/4”	0.10 – 0.25 lbs./sq.ft.
Topcoat - Diamapro Systems® Diamapro-Thane HPU	10-20mils 80-160 sq.ft./gal.
(Optional) Diamapro Systems® Diamapro-Thane NGU Topcoat	4-5mils 320–400 SF/gal

*NOTE: Coverage rates are for estimating purposes only. Factors such as waste, unusual/abnormal substrate conditions, and other unforeseen job-site conditions may affect actual product yields and are the responsibility of the installer.*

### APPLICATION GUIDELINES

- DO NOT apply under direct sunlight.
- DO NOT install during inclement weather.
- Primer
  - For very porous substrates.
  - For moisture vapor levels over 15 lbs., consult with the Diamapro Systems® Technical Advisor for additional information.
- Base Coat – Diamapro Systems® Diamapro-Flow RC Slow Cure
  - With the appropriate notched squeegee, spread material evenly over the entire area at 8-12 mils. Directly over the prepared substrate.
  - Back-roll with 3/8” microfiber roller cover removing all squeegee lines.
  - Keep a wet edge while applying products.
  - Wear spiked shoes when walking on material.
  - Do NOT let material puddle on floor.
- Decorative Flake
  - Pour the flake into multiple 5-gallon buckets for distribution.
  - Wearing spiked shoes, walk to the area first coated with the base coat and broadcast the flake into the wet base coat.
  - While broadcasting, gradually fill the floor swiftly.
  - Once the floor has been completely covered in flake, walk back out onto the floor and cover all the areas that are showing the base coat.
  - Allow to cure.
- Scrape the floor.
  - When applying flake, not all will adhere into the base coat and needs to be removed.
  - With a wide, steel bade on a pole, scrape the entire surface. This will sheer the flake flat while removing partially bonded material. Vacuum the entire area extracting all loose flake.
- High Wear Topcoat: Diamapro Systems® Diamapro-Thane NGU
  - **Diamapro Systems® Diamapro-Thane NGU** is a UV stable, urethane increasing abrasion and chemical resistance.

# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

- **Diamapro Systems® Diamapro-Thane NGU** is applied in lieu of **Diamapro Systems® Diamapro-Poly**
- Within the “Recoat Time” for the initial **Diamapro Systems® Diamapro-Poly** Topcoat, apply one coat of mixed material.
- Once mixed, pour the material in even rows along the substrate.
- Using a flat squeegee, pull the material uniformly over the grouted floor.
- Back-roll with 3/8” microfiber roller cover removing all squeegee lines producing a uniform film thickness.
- Keep a wet edge while applying material.
- Wear spiked shoes when walking on the wet material.
- Do NOT allow the material to puddle on floor.
- Allow to cure.
- Optional High-Performance Finish: **Diamapro Systems® Diamapro-Thane HPU**
  - **Diamapro Systems® Diamapro-Thane HPU** is a UV stable, urethane increasing abrasion and chemical resistance.
  - **Diamapro Systems® Diamapro-Thane HPU** MUST be applied over a **Diamapro Systems® Diamapro-Poly** grout coat.
  - Within the “Recoat Time” for the initial **Diamapro Systems® Diamapro-Poly** grout coat, apply one coat of mixed material.
  - Once mixed, pour the material in even rows along the substrate.
  - Using a flat squeegee, pull the material uniformly over the grouted floor.
  - Back-roll with 3/8” microfiber roller cover removing all squeegee lines producing a uniform film thickness.
  - Keep a wet edge while applying material.
  - Wear spiked shoes when walking on the wet material.
  - Do NOT allow the material to puddle on floor.
  - Allow to cure.

### CLEAN UP

- Allow the unused material to cure in the mixing vessels.
  - Discard the vessels according to the Federal, State and Local regulations.
- Uncured material can be cleaned up using **Diamapro Systems® Diamapro-Solvent VOC**.
  - Properly discard any rags that might have been used.
- Cured material needs to be mechanically removed from mixing paddles.

# Diama-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### MAINTENANCE AND CLEANING

- Daily
  - Sweep, removing all abrasives.
  - Remove stain producing liquids as soon as they happen.
- Auto-scrubber
  - Fit with a soft, non-abrasive white pad.
  - Use **DiamaPro Systems® Diama-Clean 30** in the freshwater tank according to the materials dilution rate.
- Mop and Bucket
  - Use **DiamaPro Systems® Diama-Clean 30** diluted in the freshwater.

### AVAILABILITY

**DiamaPro Systems® Diama-Flake Industrial System** is only available through **DiamaPro Systems®** Authorized Distributors. Only **DiamaPro Systems® Trained-Applicators** are allowed to install the system. For a list of Authorized Distributors or Applicators please contact **DiamaPro Systems®**.

### CONDITIONS OF SALE / LIMITED WARRANTY

**DiamaPro Systems®** warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. In as much as the use of **DiamaPro Systems®** product by others and other factors affecting product performance are beyond **DiamaPro Systems®** control, **DiamaPro Systems®** does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose.

SHOULD ANY **DiamaPro Systems®** NOT MEET INDUSTRY STANDARDS, **DiamaPro Systems®** WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF DIAMAPRO SYSTEMS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.

**DiamaPro Systems®** does not authorize any person to assume any other liability in connection with the sale or use of its products unless specifically authorized by **DiamaPro Systems®** in writing.



# Diamapro-Industrial Flake System

## SYSTEM DATA SHEET

Version Number: 100-04

### TECHNICAL SERVICES

The **Diamapro Systems**® office offers assistance with specifications, performance test data and field services.

### DISCLAIMER

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers.

The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products.

**FOR INDUSTRIAL AND COMMERCIAL USE ONLY**